

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 279 682 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
29.01.2003 Bulletin 2003/05

(51) Int Cl.7: **C08F 8/00, A61K 9/16**

(21) Application number: **02013696.6**

(22) Date of filing: **20.06.2002**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

- **Kang, Hyung Seok**
Yongin-shi, Kyunggi-do 449-900 (KR)
- **Han, Sang Hoon**
Suwon-shi, Kyunggi-do 440-320 (KR)
- **Chang, Ih Seop**
703 Suji-eup, Yongin-shi, Kyunggi-do (KR)

(30) Priority: **23.06.2001 KR 2001036048**

(71) Applicant: **PACIFIC CORPORATION**
Seoul (KR)

(74) Representative: **Maisch, Thomas, Dr. rer. nat.**
Ullrich & Naumann,
Patent- und Rechtsanwälte,
Luisenstrasse 14
69115 Heidelberg (DE)

(72) Inventors:
• **Nam, Yoong Sung**
449-840 Suji-eup, Yongin-shi Kyunggi-do (KR)

(54) **Amphiphilic biodegradable block copolymers and self-assembled polymer aggregates formed from the same in aqueous milieu**

(57) There are provided amphiphilic biodegradable block copolymers comprising polyethylenimine (PEI) as a hydrophilic block and aliphatic polyesters as a hydrophobic block, which can form various size of polymer aggregates and have very low critical micelle concentration, approximately $10^{-3}\text{g}/\ell$ in comparison with low-

molecular-weight micelle, and self-assembled polymer aggregates formed from the block copolymers in aqueous milieu, which can be applied to solubilization of insoluble drug and a delivery system of proteins, genes or drugs.

EP 1 279 682 A1

Description

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] The present invention relates generally to amphiphilic biodegradable block copolymers and self-assembled polymer aggregates formed from the same in aqueous milieu. More particularly, the present invention relates to amphiphilic biodegradable block copolymers comprising polyethylenimine (PEI) as a hydrophilic block and aliphatic polyesters as a hydrophobic block, and self-assembled polymer aggregates formed from the block copolymers in aqueous milieu.

2. Description of the Related Arts

[0002] Recently, nanostructured materials have received much attention as a potentially effective drug carrier. Therefore, various amphiphilic polymers comprising both a hydrophobic block and a hydrophilic block have been synthesized in order to develop effective nanostructures. In aqueous milieu, the hydrophobic compartment of an amphiphilic polymer has a tendency to self-assemble in order to avoid water and to minimize free interfacial energy of the system. By this hydrophobic interaction, the amphiphilic polymers form self-assembled aggregates in aqueous milieu. In addition, the hydrophilic blocks are uniformly dissolved in aqueous milieu and thereby the aggregates maintain a thermodynamically stable structure.

[0003] As compared with conventional low-molecular-weight micelles, polymer aggregates can form a more stable structure by chain entanglement and crystallinity of polymers, which is the reason why synthetic polymers have been extensively used as a material for drug delivery vehicles. Particularly, because the formed structure is uniform and nano-scale, it can be applied as a targetable drug delivery system, a carrier micelle for solubilizing insoluble drugs, and a gene delivery system.

[0004] These amphiphilic polymers exhibit various properties depending on their component blocks. For example, physicochemical properties of amphiphilic polymers and structures formed therefrom are determined by a molecular weight of the polymer, a ratio of hydrophilic/hydrophobic blocks, rigidity of blocks, affinity between blocks, molecular structure of blocks, charge density of a hydrophilic block, addition of ligands, etc.

[0005] In connection with a drug delivery system, many studies have been conducted on hydrophilic polymers. Hydrophilic polymers such as poly(ethylene oxide) (PEO) or poly(ethylene glycol) (PEG) have an excellent biocompatibility. In particular, there are many reports regarding the addition of poly(ethylene oxide) into various hydrophobic blocks.

[0006] For example, R. Langer of MIT synthesized polymer nanoparticles comprising polyethylene oxide as a hydrophilic block and biodegradable polyester as a hydrophobic block. The polyesters such as polylactide or poly(D,L-lactide-co-glycolide) was approved as a biodegradable and biocompatible polymer for clinical uses by Food & Drug Administration (FDA) in USA. In this case, we can observe that poly(ethylene oxide) drifts to the surface of nanoparticles by phase separation and drug concentration effused in blood increases in comparison with that case when polymer particles without poly(ethylene oxide) was used [R. Gref, Y. Minamitake, M. T. Peracchia, V. Trubeskoy, A. Milshteyn, J. Sinkule, V. Torchilin, R. Langer, *Int. Symp. Controlled Release Mater.*, 20, 131 (1993)].

[0007] Additionally, there have been reported the preparation of self-assembled polymer aggregates using poly(ethylene oxide) as a hydrophilic block, and as for a hydrophobic block, for example, using poly(β -benzyl-L-aspartate) [G. S. Kwon, M. Naito, M. Yokoyama, T. Okano, Y. Sakurai, K. Kataoka, *Langmuir*, 9, 945 (1993)]; using poly(propylene oxide) [A. V. Kabanov, E. V. Batrakova, N. S. Neiknubanov, et al. *Journal of Controlled Release*, 22, 141 (1992)]; using poly(ϵ -caprolactone) [C. Allen, J. Han, Y. Yu, D. Maysinger, A. Eisenberg, *Journal of Controlled Release*, 63, 275 (2000)]; using oligo-methacrylate [T. Inoue, G. Chen, K. Nakamae, A. S. Hoffman, *Journal of Controlled Release*, 51, 221 (1998)]; etc.

[0008] Recently, there have been reported the preparation of polymer aggregates using ionic interactions. K. Kataoka et al. proposed a novel concept of polymer aggregates, "polyion complex (PIC) micelles" formed by ionic bonding between polymers having counter ions, by using both poly(ethylene oxide)-poly(L-lysine) block copolymer and poly(ethylene oxide)-poly(L-aspartate) block copolymer [A. Harada and K. Kataoka, *Macromolecules*, 28, 5294 (1995)]. By using this concept, they reported that lysozyme, which is a protein having an isoelectric point of 11 and thereby has positive charge, is successfully loaded within polymer micelles [A. Harada and K. Kataoka, *Macromolecules*, 31, 288 (1998)].

[0009] In addition to core-shell type polymer micelles using poly(ethylene oxide), there have been many concerns on structures such as cylindrical micelles, hollow vesicles, hollow hoops, etc. Adi Eisenberg (McGill University in Canada) reported various types of polymer aggregates using poly(ethylene oxide)-polystyrene copolymer [K. Yu and A. Eisenberg, *Macromolecules*, 29, 6359 (1996)]. In addition, D. E. Discher and D. Hammer (Pennsylvania University in

USA) proposed a novel vesicular structure, "polymersome" using poly(ethylene oxide)-poly(ethylethylene) block copolymer [BM Discher, YY Won, D. S. Ege, J. C-M. Lee, F. S. Bates, D. E. Discher, D. A. Hammer, *Science*, 284, 113 (1999)].

[0010] All the above polymer aggregates use poly(ethylene oxide) as a corona block in consideration that poly(ethylene oxide) is a nonionic polymer without reactivity with in vivo biological molecules and particularly, poly(ethylene oxide) having molecular weight of 5,000 or less can be filtrated at kidney to be discharged to the exterior. Thanks to such an excellent biocompatibility of poly(ethylene oxide), polymer aggregates using poly(ethylene oxide) have been extensively considered as a polymer material for drug delivery system. In particular, because poly(ethylene oxide) inhibits protein adsorption, polymer aggregation can be prevented from interaction with in vivo molecules in blood, thereby can be protected from removal by immunocytes such as mononuclear phagocyte system (MPS) and can stay in blood for a long time.

[0011] However, poly(ethylene oxide) does not have other functional groups except terminal groups, so to be limited to attach cell-adhesion molecules in application of a targetable drug delivery system. In addition, in application of oral or percutaneous administration, it is difficult to increase penetration into the tissue due to a large hydrodynamic volume of poly(ethylene oxide). Besides, there is a limitation in forming various structures of polymer aggregates. In addition, there is defect that block length has to be longer for forming polymer aggregates in comparison with ionic polymers, so that the volume of core part to contain drug is relatively small. Therefore, there have been needs for novel polymer aggregates using another polymers different from poly(ethylene oxide), depending on drug administration routes.

[0012] Aggregates formed from polymer electrolytes have been applied as a gene delivery carrier. However, electric charge of the polymer is used in coupling between a polymer and a gene, and therefore, it does not determine surface property of the aggregates.

[0013] Adi Eisenberg et al. (McGill University, Canada) reported various structures having a charged hydrophilic polymer as a corona block, wherein the charged polymer exists on the surface of the self-assembled aggregates. He employed polystyrene as a hydrophobic block and poly(acrylic acid) as a hydrophilic block. In this case, polymer aggregates can be formed from poly(acrylic acid) having much lower molecular weight compared with the conventional corona block such as poly(ethylene oxide). This structure is named as "crew-cut" polymer aggregates [L. Zhang and A. Eisenberg, *Science*, 268, 1728 (1995); L. Zhang, K. Yu, A. Eisenberg, *Science*, 272, 1777 (1996); L. Zhang and A. Eisenberg, *Macromolecules*, 29, 8805 (1996)]. In this case, the length of hydrophobic blocks can be controlled to be relatively longer and various types of structures can be formed depending on block length or molecular weight of polymer, condition of aqueous milieu, etc. [C. Allen, D. Maysinger, A. Eisenberg, *Colloids and Surfaces B: Biointerfaces*, 16, 3 (1999)]. However, polystyrene is not a biocompatible polymer and has difficulty in removal after injection into the body.

[0014] Therefore, a biocompatible polymer is required in order to be applied as a drug delivery system. Biocompatible polymers must not cause in vivo inflammation or immune reaction, must be biodegraded in vivo to be easily removed, and degradation products thereof must be harmless in vivo. As a polymer satisfying these conditions, biodegradable aliphatic polyesters using lactic acid or glycolic acid as monomer units were approved by FDA. Aliphatic polyester has been extensively used as a drug delivery carrier or a surgical suture, and has been verified biocompatible.

[0015] Under this circumstances, in order to solve the above-mentioned problems, the present inventors have conducted extensive studies on novel polymer aggregates using other polymer different from poly(ethylene oxide) as a hydrophilic block. As a result thereof, they found that polymer aggregates comprising cationic polyethylenimine as a hydrophilic block and an aliphatic polyester with biodegradability and biocompatibility as a hydrophobic block can satisfy the above object.

SUMMARY OF THE INVENTION

[0016] Therefore, one object of the present invention is to provide biodegradable block copolymers comprising polyethylenimine as a hydrophilic block and aliphatic polyesters as a hydrophobic block and to provide polymer aggregates formed therefrom.

[0017] Another object of the present invention is to provide multifunctional block copolymers to be applied in vivo utilizing electric charges and functional group of hydrophilic block.

[0018] These and other objects and advantages of the present invention will become apparent to the skilled in the art from the following detailed description as considered in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0019] FIG. 1a is an infrared spectrum of typical poly(D,L-lactide-co-glycolide) ($M_n = 11,000$).

[0020] FIG. 1b is an infrared spectrum of the linear polyethylenimine ($M_n=400$) -poly(D,L-lactide-co-glycolide) ($M_n=11,000$) block copolymer prepared in Example 1.

[0021] FIG. 2 is a carbon nuclear magnetic resonance (^{13}C NMR) spectrum (in deuterated dimethylsulfoxide) of the linear polyethylenimine ($M_n=400$)-poly(D,L-lactide-co-glycolide) ($M_n = 11,000$) block copolymer prepared in Example 1.

[0022] FIG. 3 is a result of gel permeation chromatography (GPC) analysis for the branched polyethylenimine ($M_n = 600$)-poly(D,L-lactide-co-glycolide) ($M_n = 11,000$) block copolymer prepared in Example 2.

[0023] FIG. 4 is results of differential scanning calorimetry (DSC) analysis for the linear and the branched polyethylenimine-poly(D,L-lactide-co-glycolide) block copolymers prepared in Examples 3 and 4, respectively, wherein,

A is a result for poly(D,L-lactide-co-glycolide);

B is a result for polyethylenimine-poly(D,L-lactide-co-glycolide) (Ex. 3);

and

C is a result for polyethylenimine-poly(D,L-lactide-co-glycolide) (Ex. 4).

[0024] FIG. 5 is a pyrene fluorescence spectrum of each concentration of the aggregates depending on wavelength in aqueous solution of the linear polyethylenimine ($M_n=400$)-poly(D,L-lactide-co-glycolide) ($M_n=25,000$) prepared in Example 3.

[0025] FIG. 6 is ratios of fluorescence intensities at 337 nm and at 334 nm depending on concentrations of the aggregates in aqueous solution of the linear polyethylenimine ($M_n=400$)-poly(D,L-lactide-co-glycolide) ($M_n=25,000$) prepared in Example 3.

[0026] FIG. 7 is a result of dynamic light scattering analysis for the aggregates of the linear polyethylenimine ($M_n=400$)-poly(D,L-lactide-co-glycolide) ($M_n=25,000$) prepared in Example 3.

[0027] FIG. 8 is a result of transmission electron microscopy (TEM) analysis for the aggregates of the linear polyethylenimine ($M_n=400$)-poly(D,L-lactide-co-glycolide) ($M_n = 25,000$) prepared in Example 3.

DETAILED DESCRIPTION OF THE INVENTION

[0028] The following is a detailed description of the present invention.

[0029] The present invention is characterized in that block copolymers comprise a cationic polymer and a biodegradable polymer. More particularly, the present invention is characterized in that block copolymers comprise cationic polyethylenimine (PEI) as a hydrophilic block and biodegradable aliphatic polyester as a hydrophobic block. Further, the present invention provides self-assembled polymer aggregates formed from said block copolymers in an aqueous solution.

[0030] In this specification, the term "polymer" refers to a synthetic macromolecule and oligomer, and the term "polymer aggregate" refers to a structure formed by self-assembly of polymer, for example, nanoparticles, micelles, vesicles, cylinders, etc.

[0031] Said biodegradable aliphatic polyester employed as a hydrophobic block may be one selected from the group consisting of poly(L-lactide), poly(D,L-lactide), poly(D-lactide-co-glycolide), poly(L-lactide-co-glycolide), poly(D,L-lactide-co-glycolide), polycaprolactone, polyvalerolactone, polyhydroxybutyrate, polyhydroxyvalerate, poly(1,4-dioxan-2-one), polyorthoester and copolymers therebetween.

[0032] Poly(D,L-lactide-co-glycolide) (PLGA) may be preferably selected, because biodegradable polymer having various degradation rate can be obtained by controlling monomer ratio of lactic acid and glycolic acid or by controlling polymerization conditions.

[0033] Further, said block copolymer can be obtained by covalent bond between polyethylenimine and aliphatic polyester, for example, ester bond, anhydride bond, carbamate bond, carbonate bond, imine or amide bond, secondary amine bond, urethane bond, phosphodiester bond or hydrazone bond. In addition, it may be A-B type of double blocks wherein A is said hydrophobic block of aliphatic polyester and B is said hydrophilic block of polyethylenimine.

[0034] In said block copolymer, weight ratio of aliphatic polyester and polyethylenimine may be preferably in a range of 100:1 ~ 1:10. If the amount of polyester is excessive, the block copolymer cannot form stable aggregates and thereby precipitated. If the amount of polyethylenimine is excessive, core part to contain drug decreases. Accordingly, it may be preferable to limit the ratio in said range.

[0035] Said biodegradable polymer may be employed regardless of molecular weights. Preferably, said biodegradable hydrophobic polyester having 1,000 ~ 70,000 of weight average molecular weight (M_w) may be employed. As for said polyethylenimine, it may be effective in forming aggregates to employ hydrophilic polymer of which M_w is 100 ~ 10,000.

[0036] As a method for forming polymer aggregates in aqueous phase by using biodegradable block copolymers proposed by the present invention, there are a method wherein said block copolymers are directly dispersed in aqueous phase and then ultrasonic wave is irradiated; a method wherein said block copolymers are dispersed or dissolved in organic solvent and then the solvent is extracted with excess of distilled water or evaporated; a method wherein said

block copolymers are dispersed or dissolved in organic solvent and then the solvent is evaporated by strongly stirring with a homogenizer or a high-pressure homo-mixer; a method wherein said block copolymers are dispersed or dissolved in organic solvent and then is dialyzed with excess of distilled water; and a method wherein said block copolymers are dispersed or dissolved in organic solvent and then distilled water is added thereto.

[0037] In detail, the method for preparing polymer aggregates according to the present invention comprises the following steps of:

(1) dissolving or dispersing said block copolymers in organic solvent and then adding distilled water thereto, to induce phase separation of polymers;

(2) forming aggregates from the block copolymer solution or dispersion of said step (1) by any one method selected from the group consisting of aqueous addition; solvent evaporation; dialysis; phase transition precipitation; ultrasonic irradiation; heating method; stirring method; high-pressure homogenization; and combination therebetween; and

(3) filtrating said block copolymer solution or dispersion and then freeze drying to give block copolymer powder.

[0038] An organic solvent employed in preparing polymer aggregates by using the present biodegradable block copolymer in aqueous phase may be one or more selected from the group consisting of acetone, dimethylsulfoxide, dimethylformamide, N-methylpyrrolidone, dioxane, tetrahydrofuran, ethyl acetate, acetonitrile, methylethyl ketone, methylene chloride, chloroform, methanol, ethanol, ethyl ether, diethyl ether, hexane and petroleum ether.

[0039] In case of pharmaceutical or cosmetic application, it may be preferable to limit the size of said aggregates in a range of 10~1,000nm, in consideration of penetration into the skin and loading of active ingredients.

[0040] The nano-scale polymer aggregates obtained in the present invention have very low critical micelle concentration, approximately 0.1~10mg/l and are extraordinarily stable in aqueous phase, in comparison with low-molecular-weight micelles. These characteristics enable the present polymer aggregates to maintain their structures in aqueous phase or in vivo after long-term preservation. Therefore, the present polymers have good property as a drug delivery vehicle.

[0041] Although said polyethylenimine is classified into linear polymer and branched polymer, it can form polymer aggregates regardless of its structures. The range of molecular weight of polyethylenimine depends on the molecular weight of biodegradable polyesters selected. In general, it may be preferable to employ polyethylenimine having 5,000 or less of molecular weight.

PREFERRED EMBODIMENT OF THE INVENTION

[0042] The present invention will be described in more detail by way of the following examples, which should not be considered to limit the scope of the present invention.

<Example 1>

Linear polyethylenimine(Mn=400)-poly(D,L-lactide-co-glycolide) (Mn =11,000) block copolymer (carbamate bond)

[0043] 50ml of dimethylformamide and 145mg of N,N-carbonyldiimidazole (CDI) were introduced into the reactor and then stirred uniformly. Thereto was added 5g of poly(D,L-lactide-co-glycolide) (RG502, Boehringer Ingelheim, Germany), to activate its terminal hydroxy group. To said solution was added 500mg of linear polyethylenimine(number-average molecular weight : Mn=400) and then, stirred under condition of 1 atm and room temperature. After 12 hours, the resultant was filtrated with nylon filter with 0.45μm of pore, and then dispersed in tertiary distilled water to remove residue reactant and reagent by dialysis.

[0044] Molecular-weight distribution of the obtained polymer was analyzed by gel permeation chromatography. The result confirmed that the obtained polymer exhibits single distribution of molecular weight.

[0045] Specific peaks of amine and ester were analyzed by means of infrared spectroscopy. The results are shown in FIG. 1.

[0046] Identification of the obtained polymer was analyzed by carbon nuclear magnetic resonance spectroscopy in deuterated dimethylsulfoxide. The result is shown in FIG. 2. The result identified the obtained polymer as polyethylenimine(PEI)-poly(D,L-lactide-co-glycolide) copolymer.

[0047] Thermal property of the polymer was analyzed by means of differential scanning calorimetry (DSC2010, TA Instruments). Heating was performed by 10°C per minute in a range of -100~100°C. Glass transition temperature(Tg) was determined by exothermal curve output in the secondary heating. Tg of pure poly(D,L-lactide-co-glycolide) before reaction is 42.2°C and Tg of the linear polyethylenimine(Mn=400)-poly(D,L-lactide-co-glycolide) (Mn =11,000) prepared in this example is 31.75 °C.

<Example 2>

Branched polyethylenimine(Mn=600)-poly(D,L-lactide-co-glycolide) (Mn =11,000) block copolymer (carbamate bond)

5 [0048] 50ml of Dimethylformamide and 145mg of N,N-carbonyldiimidazole were introduced into the reactor and then stirred uniformly. Thereto was added 5g of poly(D,L-lactide-co-glycolide) (RG502), to activate its terminal hydroxy group. To said solution was added 500mg of branched polyethylenimine(Mn=600) and then, stirred under condition of 1 atm and room temperature. After 12 hours, the resultant was filtrated with nylon filter with 0.45µm of pore, and then dispersed in tertiary distilled water to remove residue reactant and reagent by dialysis.

10 [0049] As shown in FIG. 3, gel permeation chromatography analysis confirmed that the obtained polymer exhibits single distribution of molecular weight.

[0050] Specific peaks of amine and ester were analyzed by means of infrared spectroscope, and identification of the obtained polymer was analyzed by carbon nuclear magnetic resonance spectroscopy in deuterated dimethylsulfoxide. The results identified the obtained polymer as polyethylenimine-poly-D,L-lactide-co-glycolide copolymer.

15 [0051] Thermal property of the polymer was analyzed by means of differential scanning calorimetry. Tg of pure poly (D,L-lactide-co-glycolide) before reaction is 42.2 °C and Tg of the branched polyethylenimine(Mn=600)-poly-D,L-lactide-co-glycolide(Mn=11,000) prepared in this example is 37.6°C.

<Example 3>

Linear polyethylenimine(Mn=400)-poly(D,L-lactide-co-glycolide) (Mn =25,000) block copolymer (amide bond)

20 [0052] 100ml of Dimethylformamide, 123mg of dicyclohexyl carbodiimide (DCC) and 70mg of N-hydroxysuccinimide (NHS) were introduced into the reactor and then stirred uniformly. Thereto was added 5g of poly(D,L-lactide-co-glycolide) (RG503H), to activate its terminal hydroxy group. To said solution was added 0.8g of linear polyethylenimine (Mn=400) and then, stirred under condition of 1 atm and room temperature. After 12 hours, the resultant was filtrated with nylon filter with 0.45µm of pore, and then dispersed in tertiary distilled water to remove residue reactant and reagent by dialysis.

30 [0053] Gel permeation chromatography analysis confirmed that the obtained polymer exhibits single distribution of molecular weight.

[0054] Specific peaks of amine and ester were analyzed by means of infrared spectroscope, and identification of the obtained polymer was analyzed by carbon nuclear magnetic resonance spectroscopy in deuterated dimethylsulfoxide. The results identified the obtained polymer as polyethylenimine-poly-D,L-lactide-co-glycolide copolymer.

35 [0055] Thermal property of the polymer was analyzed by means of differential scanning calorimetry. As shown in FIG. 4, Tg of pure poly-D,L-lactide-co-glycolide before reaction is 43.9°C and Tg of the linear polyethylenimine (Mn=400)-poly(D,L-lactide-co-glycolide) (Mn =25,000) prepared in this example is 37.6°C.

<Example 4>

Branched polyethylenimine(Mn=600)-poly(D,L-lactide-co-glycolide) (Mn =25,000) block copolymer (amide bond)

40 [0056] 100ml of Dimethylformamide, 123mg of dicyclohexyl carbodiimide and 70mg of N-hydroxysuccinimide were introduced into the reactor and then stirred uniformly. Thereto was added 5g of poly(D,L-lactide-co-glycolide) (RG503H), to activate its terminal hydroxy group. To said solution was added 0.8g of branched polyethylenimine (Mn=600) and then, stirred under condition of 1 atm and room temperature. After 12 hours, the resultant was filtrated with nylon filter with 0.45µm of pore, and then dispersed in tertiary distilled water to remove residue reactant and reagent by dialysis.

[0057] Gel permeation chromatography analysis confirmed that the obtained polymer exhibits single distribution of molecular weight.

50 [0058] Specific peaks of amine and ester were analyzed by means of infrared spectroscope, and identification of the obtained polymer was analyzed by carbon nuclear magnetic resonance spectroscopy in deuterated dimethylsulfoxide. The results identified the obtained polymer as polyethylenimine-poly-D,L-lactide-co-glycolide copolymer.

55 [0059] Thermal property of the polymer was analyzed by means of differential scanning calorimetry. As shown in FIG. 4, Tg of pure poly-D,L-lactide-co-glycolide before reaction is 43.9°C and Tg of the branched polyethylenimine (Mn=600)-poly(D,L-lactide-co-glycolide) (Mn =25,000) prepared in this example is 20.25°C.

<Example 5> Preparation of polymer aggregates

[0060] 25mg of each sample of the block copolymers prepared in Examples 1~4 was uniformly dispersed in 0.5 ml of acetone and then gradually added into 10ml of tertiary distilled water under stirring. Each sample was evaporated in chemical hood for 12 hours to remove acetone. Subsequently, each sample was diluted with deionized and tertiary distilled water to a concentration range of 2.5g/l~0.0001g/l, in detail, 2.5g/l, 6.25×10^{-1} g/l, 3.13×10^{-1} g/l, 1.56×10^{-1} g/l, 7.81×10^{-2} g/l, 3.91×10^{-2} g/l, 1.95×10^{-2} g/l, 9.77×10^{-3} g/l, 4.88×10^{-3} g/l, 2.44×10^{-3} g/l, 1.22×10^{-3} g/l, 6.10×10^{-4} g/l, 3.05×10^{-4} g/l, 1.53×10^{-4} g/l and 7.63×10^{-5} g/l.

[0061] Critical micelle concentration was measured by fluorescence peak analysis of pyrene. Firstly, pyrene was dissolved in acetone to give 6×10^{-7} M of solution. The solution was introduced into eppendorf tube by 1 ml per tube. The acetone was evaporated in chemical hood for 12 hours to be removed. Into the eppendorf tube was added said 2.5g/l~0.0001g/l of polymer aggregates solution and then stood at a temperature of 37°C for 4 hours. Fluorescence peak analyzer was Hitachi F-4500 (Nissei Sangyo Co., Ltd, Tokyo, Japan). Slit spacing was 5 at both excitation and emission, scanning velocity was 240nm/min, and PMT voltage was 400V. Emission wavelength was fixed at 390nm and excitation wavelength was scanned from 300nm to 360nm. The pyrene fluorescence spectrum of each concentration of the aggregates is shown in FIG. 5. Critical micelle concentration was determined by ratios of fluorescence intensities at 337nm and at 334nm (I_{337nm}/I_{334nm}) depending on concentrations of the micelle, as shown in FIG. 6.

[0062] Average particle diameters of the polymer aggregates prepared in Examples 1~4 were obtained by dynamic light scattering (DLS) analysis, as shown in FIG. 7. The concentration of the aggregates was 0.6mg/ml and scattering angle was fixed at 90°.

[0063] The critical micelle concentration, the average particle diameter and the dispersivity of the polymer aggregates are shown in Table 1.

[Table 1]

	Critical micelle concentration (mg/l)	Average particle diameter (nm)	Dispersivity
Ex. 1	2.54	188.3	0.10
Ex. 2	1.45	161.1	0.12
Ex. 3	1.54	166.2	0.11
Ex. 4	2.17	136.7	0.14

[0064] Morphology of the polymer aggregates prepared in Examples 1~4 was analyzed by means of transmission electron microscopy (TEM, JEOL 2010). The sample was put on 100mesh of copper grid coated with carbon, and dyed with 2% of uranyl acetate solution. Magnification was 1,000,000. The result is shown in FIG. 8.

[0065] As shown by the above results, the present amphiphilic biodegradable block copolymers comprising biodegradable aliphatic polyester as a hydrophobic block and polyethylenimine as a hydrophilic block have particle properties as above-described, so to be employed as appropriate vehicles in forming structures to load water-soluble or hydrophobic drug within inner core or hydrophobic region.

[0066] As confirmed by the above description, the polyethylenimine-polyester block copolymers according to the present invention can form various size of polymer aggregates and have very low critical micelle concentration, approximately 0.001~0.005g/l. And, the transmission electron microscopy analysis confirmed that the polymer aggregates are sphere. Therefore, the present block copolymers can form structures capable of loading water-soluble or hydrophobic drug within inner core or hydrophobic region. The polymer aggregates formed from the present block copolymers are expected to accelerate solubilization of insoluble drug and oral or percutaneous penetration, and to be applied as delivery vehicle of protein, gene or drug having electric charge.

[0067] Although preferred embodiments of the present invention have been described in detail hereinabove, it should be clearly understood that many variations of the basic inventive concepts herein taught which may appear to those skilled in the art will still fall within the spirit and scope of the present invention as defined in the appended claims.

Claims

1. Amphiphilic biodegradable block copolymer comprising a biodegradable aliphatic polyester as a hydrophobic block and polyethylenimine as a hydrophilic block.
2. The block copolymer according to Claim 1, wherein said biodegradable aliphatic polyester is one or more selected

from the group consisting of poly(L-lactide), poly(D,L-lactide), poly(D-lactide-co-glycolide), poly(L-lactide-co-glycolide), poly(D,L-lactide-co-glycolide), polycaprolactone, polyvalerolactone, polyhydroxybutyrate, polyhydroxyvalerate, poly(1,4-dioxan-2-one), polyorthoester and copolymers therebetween.

- 5 **3.** The block copolymer according to Claim 1, wherein said polyethylenimine and said aliphatic polyester are bonded by a covalent bond that selected from the group consisting of ester bond, anhydride bond, carbamate bond, carbonate bond, imine or amide bond, secondary amine bond, urethane bond, phosphodiester bond and hydrazone bond.
- 10 **4.** The block copolymer according to Claim 1, wherein said polyethylenimine and said aliphatic polyester are composed of A-B type of double blocks, wherein A is hydrophobic block of aliphatic polyester and B is hydrophilic block of polyethylenimine.
- 15 **5.** The block copolymer according to Claim 1, wherein weight ratio of said aliphatic polyester and said polyethylenimine is in a range of 100:1 ~ 1:10.
- 6.** The block copolymer according to Claim 1, wherein said aliphatic polyester has 1,000~ 70,000 of weight-average molecular weight.
- 20 **7.** The block copolymer according to Claim 1, wherein said polyethylenimine has 100~ 10,000 of weight-average molecular weight.
- 8.** A method for preparing amphiphilic block copolymer aggregates, which comprises the following steps of:
 - 25 (1) dissolving or dispersing the block copolymers according to any one of Claims 1 to 7 in organic solvent and then adding distilled water thereto, to induce phase separation of polymers;
 - (2) forming aggregates from the block copolymer solution or dispersion of said step (1) by any one method selected from the group consisting of aqueous addition; solvent evaporation; dialysis; phase transition precipitation; ultrasonic irradiation; heating method; stirring method; high-pressure homogenization; and combination therebetween; and
 - 30 (3) filtrating said block copolymer solution or dispersion and then freeze drying to give block copolymer powder.
- 9.** The method according to Claim 8, wherein said organic solvent employed in preparing polymer aggregates is one or more selected from the group consisting of acetone, dimethylsulfoxide, dimethylformamide, N-methylpyrrolidone, dioxane, tetrahydrofuran, ethyl acetate, acetonitrile, methylethyl ketone, methylene chloride, chloroform, methanol, ethanol, ethyl ether, diethyl ether, hexane and petroleum ether.
- 35 **10.** Amphiphilic block copolymer aggregates prepared by dispersing said block copolymers according to any one of Claims 1 to 7 in a solvent.
- 40 **11.** The aggregates according to Claim 10, of which average particle diameter is in a range of 10~1,000nm.

FIGURES

FIG. 1a




FIG. 1b




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7





FIG. 8



BEST AVAILABLE CO.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 01 3696

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 417 982 A (MODI PANKAJ) 23 May 1995 (1995-05-23) * column 3, line 15 - line 27; claim 26 *	1-11	C08F8/00 A61K9/16
A	DE 199 16 384 A (SCHERING AG) 5 October 2000 (2000-10-05) * column 3, line 31 - line 39; claims *	1-11	
A	DE 199 30 729 A (GOEPFERICH ACHIM) 11 January 2001 (2001-01-11) * claims *	1-11	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08L C08F A61K
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 3 December 2002	Examiner Iraegui Retolaza, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (03.82) (PC-A201)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 01 3696

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

03-12-2002

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 5417982	A	23-05-1995	AT	173160 T	15-11-1998
			AU	1702395 A	04-09-1995
			CA	2180424 A1	24-08-1995
			WO	9522318 A1	24-08-1995
			DE	69505949 D1	17-12-1998
			DE	69505949 T2	02-06-1999
			DK	744940 T3	26-07-1999
			EP	0744940 A1	04-12-1996
			JP	9509161 T	16-09-1997

DE 19916384	A	05-10-2000	DE	19916384 A1	05-10-2000

DE 19930729	A	11-01-2001	DE	19930729 A1	11-01-2001
			AU	6688900 A	22-01-2001
			WO	0102460 A1	11-01-2001
			EP	1198488 A1	24-04-2002

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

100